

Injection Wax Properties Comparison Chart

Injection Wax	Flow Temp	Injection Pressure	Flow	Carveability	Flexibility	Shrinkage	Memory	Shelf Life
Joe's New Injection Wax™ Red	155-160°F/ 68-71°C	3-15psi	high	medium	high	low	high	medium
Joe's New Injection Wax™ Aqua	155-160°F/ 68-71°C	3-15psi	high	medium	high	low	high	medium
Joe's New Injection Wax™ Turquoise	155-160°F/ 68-71°C	3-15psi	high	medium	high	low	high	medium
Joe's New Injection Wax™ Pink	160-165°F/ 71-74°C	3-15psi	high	medium	high	low	high	high
Joe's New Injection Wax™ Plastiflex	160-165°F/ 71-74°C	3-15psi	medium	low	high	low	high	high
Caster's Choice™ Precision Pink	155-180°F/ 68-82°C	3-15psi	high	low	high	low	high	high
Caster's Choice™ Blue	150-180°F/ 66-82°C	3-15psi	medium	low	medium	low	high	medium
Caster's Choice™ Aqua	155-180°F/ 68-82°C	3-15psi	high	low	high	low	high	high
Caster's Choice™ Red	155-180°F/ 68-82°C	3-15psi	high	low	high	low	high	high
Magna-Ject™ Pink	156-158°F/ 69-70°C	3-15psi	high	medium	high	low	high	high
Rio buckle	155-160°F/ 68-71°C	3-15psi	high	low	medium	low	medium	medium
Blue carveable	155-160°F/ 68-71°C	6-15psi	medium	high	low	medium	low	low
Plast-O-Wax™	155-160°F/ 68-71°C	8-20psi	medium	low	high	medium	high	high